# Clay Bodies Offered at CCW

*Updated September 2026*

## White Clays

| ID Code | Name | Qualities | Performance | Shrinkage At Δ10 |
|---|---|---|---|---|
| W | White Stoneware #510 (Laguna) | Plastic and smooth grolleg white stoneware with fine grog. | **Gas Kiln**: Pure white<br>**Noborigama Soda**: Glossy white<br>**Noborigama Salt**: Glossy white<br>**Train Kiln**: White with subtle peach flashing | 13% |
| B | B Mix Cone 10 (Laguna) | Smooth porcelain texture, easy to throw. CCW's default beginner body. | **Gas Kiln**: Off-white, warm<br>**Noborigama Soda**: Light beige to soft orange flashing<br>**Noborigama Salt**: Glossy white<br>**Train Kiln**: Orange-red flashing | 13% |
| TP | Tucker H.H. Porcelain (Tucker) | Smooth, cooperative, non-Grolleg porcelain. | **Gas Kiln**: White or warm off-white<br>**Noborigama Soda**: Glossy white, latte/egg nog flashing<br>**Noborigama Salt**: Glossy white, some carbon trapping<br>**Train Kiln**: Glossy white, peach or pale orange flashing | 14% |
| SW | Speckled White (CCW) | Hybrid studio white clay bodies with granular ilmenite added for speckle. | **Gas Kiln**: Off white, speckling appears under glazes<br>**Noborigama Soda**: Toasted almond with bronze speckle<br>**Noborigama Salt**: Beige body with metallic speckling<br>**Train Kiln**: Toasted almond, light speckling | 13% |
| K | Kyanite (Laguna custom) | White Stoneware with 100-mesh kyanite added. | CCW house Raku clay | |

**Brown Clays**

| ID Code | Name | Qualities | Performance | Shrinkage At Δ10 |
|---|---|---|---|---|
| WL | Sheffield Wood Light (Sheffield) | Formulated for wood firing. Stoneware with fine grog. Can be quick-dried. | **Gas Kiln**: Light brown, some iron speckling<br>**Noborigama Soda**: Medium brown, subtle orange peeling<br>**Noborigama Salt**: Medium brown, dramatic orange peeling<br>**Train Kiln**: Medium-dark brown, iron rich warm tones | 13% |
| S60 | Soldate 60 (Laguna) | Stoneware with coarse sand added. Great for hand building. Can be quick-dried. | **Gas Kiln**: Orange-brown<br>**Noborigama Soda**: Glossy medium brown<br>**Noborigama Salt**: medium brown w/ orange peeling<br>**Train Kiln**: Dark brown | 13.5% |
| TM | Tim's Mix Brown (CCW) | Hybrid of house clay bodies with silica sand, sawdust, and poultry grit added. | **Gas Kiln**: Pale brown, gnarly<br>**Noborigama Soda**: Medium brown, gnarly<br>**Noborigama Salt**: Glossy with some orange peeling<br>**Train Kiln**: Medium brown, great interaction with ash and vapor | 12% |
| H | B Mix Wood (Laguna) | Formulated for wood firing. Porcelain texture, easy to throw. | **Gas Kiln**: Not recommended<br>**Noborigama Soda**: Glossy orange/bronze flashing<br>**Noborigama Salt**: Bleaches to beige/white<br>**Train**: Dramatic orange to bronze flashing | 13% |